

# CARECLEAN ALKALINE

## **Powerful non-caustic alkaline cleaner**

- Removes vegetable and animal oils, fatty acid and greases, whether or not hardened or carbonised.
- Applicable at low temperatures.
- Works effectively.

## **Application**

Careclean Alkaline contains besides non-ionogene surface-active components and alkaline salts even effective solvents. This makes the products well applicable at lower temperatures (20-60°C) by means of some circulation. Careclean Alkaline is suited to remove vegetable and animal oils and greases, whether or not hardened or coarbonised. Careclean Alkaline is not suited to use on zinc silicate coatings and most paints/laquers. Diluted with water to a solution of maximum 10% and at a temperature of maximum 60°C, the product is safe to use on epoxy-coatings. It is suited to use on most metals except for aluminium, tin, zinc and galvanised material.

## **Directions for use**

### **Prewashing**

Prior to cleaning with Careclean Alkaline, it is advised to wash with hot water of approximately 80°C. In case of drying and semi-drying oils, prewashing is to be done with cold water.

### **Immersion bath**

For slight oil-contaminations Careclean Alkaline can be diluted with water to a 10% solution. Heaten the liquid with a heating coil or by means of steam injection to 20-60°C. Place the objects to be cleaned in the bath and allow several hours working time. Afterwards brush the objects while rinsing them with a powerful waterjet. In case of heavily contaminated objects, Careclean Alkaline is applied undiluted in immersion bathes, for example to remove old paint layers to and to clean oil and grease filters, deep fry equipment, baking ovens etc.

### **Spraying**

Depending on the amount and character of the contamination, Careclean Alkaline is to be used pure or diluted at a temperature of 20 - 60°C. Allow the product to work for 20 to 60 minutes and spray afterwards with a powerful high pressure waterjet. Warm water is to be preferred.

### **Recirculation**

With this method, the cleaning chemicals are added to a prior determined amount of cleaning chemicals is usually 1% of the capacity of the tank is to be cleaned.

### **Properties**

Light brown liquid. Very alkaline, contains potassium hydroxide. Suited to use on most metals, but is not to be used on tin, aluminium, zinc silicate coatings.

Specific Gravity (20°C)	: 1.06
Flash point (PMCC)	: 98°C
pH (1% Solution)	: 12.5

**Contains approximately 7% potassium hydroxide.**

*For detailed information on safety and health, please refer to Material Safety Data Sheet and / or Product label.*

The details of our products are given completely free of undertaking. Since their application lies outside our control we cannot accept any liability for the results.